



DIVERSIFIED
TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 14, 2008

LOTUS & WINDOWARE, INC.
4444 S. Mendenhall Road
Suite # 14
Memphis, TN 38141

Reference: Laboratory Test Report
Lab Identification No. 7335
Invoice No. 19672 (Attached)

One (1) blind sample, identified as **PRODUCT CODE RX1848WH, 2" PVC PLUS BLIND, WHITE, SIZE 18" WIDE X 48" LONG**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". The results are as follows:

| <u>Specimen Number</u> | <u>Residual Flame (seconds)</u> | <u>Weight Loss (percent)</u> |
|------------------------|---------------------------------|------------------------------|
| 1 | 0.0 | 35.45 |
| 2 | 0.0 | 24.78 |
| 3 | 0.0 | 34.80 |
| 4 | 0.0 | 40.94 |
| 5 | 0.0 | 38.00 |
| 6 | 0.0 | 38.45 |
| 7 | 0.0 | 35.56 |
| 8 | 0.0 | 27.99 |
| 9 | 0.0 | 35.34 |
| 10 | <u>0.0</u> | <u>39.05</u> |
| AVG. | 0.0 | 35.04 |

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment